

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61K 9/70	A1	(11) International Publication Number: WO 93/21908 (43) International Publication Date: 11 November 1993 (11.11.93)
(21) International Application Number: PCT/US93/04044 (22) International Filing Date: 29 April 1993 (29.04.93) (30) Priority data: 877,561 1 May 1992 (01.05.92) US (71) Applicant: AMGEN INC. [US/US]; Amgen Center, 1840 Dehavilland Drive, Thousand Oaks, CA 91320-1789 (US). (72) Inventors: SONG, Suk-Zu ; 12070 Alderbrook Street, Moorpark, CA 93021 (US). MORAWIECKI, Andrew ; 684 Walker Avenue, Camarillo, CA 93010 (US). (74) Agents: ODRE, Steven, M. et al.; Amgen Inc., Amgen Center, 1840 Dehavilland Drive, Thousand Oaks, CA 91320-1789 (US).		(81) Designated States: AU, CA, CZ, FI, HU, JP, KR, NO, NZ, RU, SK, UA. Published <i>With international search report.</i>
(54) Title: COLLAGEN-CONTAINING SPONGES AS DRUG DELIVERY FOR PROTEINS (57) Abstract Collagen-containing sponges comprising an absorbable gelatin sponge, collagen, and an active ingredient are disclosed as well as methods of enhancing wound healing if external and internal wounds using such sponges are disclosed.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

- 1 -

COLLAGEN-CONTAINING SPONGES
AS DRUG DELIVERY FOR PROTEINS

BACKGROUND OF THE INVENTION

5

The present invention relates to collagen containing sponges for improved sustained release delivery of pharmaceuticals.

Collagen has been used previously as a
10 component in pharmaceutical sponges. Artandi [U.S. Patent 3,157,524, issued November 17, 1964], disclosed a sponge comprised of acid treated swollen collagen. Oluwasanmi et al. [*J. Trauma* 16:348-353 (1976)]
disclosed a 1.7 millimeter thick collagen sponge that is
15 crosslinked by glutaraldehyde. Collins et al. [*Surg. Forum* 27:551-553 (1976)] disclosed an acid-swollen collagen sponge that is crosslinked by glutaraldehyde. Berg et al. [U.S. Patent 4,320,201, issued March 16, 1982], disclosed a swollen sponge of high collagen
20 purity produced by enzymatically degrading animal hides, digesting the mass in alkali or acid, mechanically comminuting the mass to produce specified lengths of collagen fibers, and crosslinking the fibers. Berg et al. [U.S. Patent 4,837,285, issued June 6, 1989],
25 disclosed porous beads that have a collagen skeleton of 1 to 30 percent of the bead volume. These beads are useful as substrates for cell growth. Doillon et al. [*Scanning Electron Microscopy III*:1313-1320 (1984)], Doillon and Silver [*Biomaterials* 7:3-8 (1986)], and
30 Doillon et al. [*Biomaterials* 8:195-200 (1987)], disclosed the growth of cells in collagen sponges with pore sizes of from about 60 to 250 μm . Some of the sponges also contained hyaluronic acid and/or fibronectin.

35

In addition, collagen has been used as a component in salves [PCT Patent Application WO 86/03122,

- 2 -

published June 5, 1986]. Collagen has also been used for wound healing in conjunction with electrical currents [Silver and Dunn, U.S. Patent 4,937,323, issued June 26, 1990].

5 In addition, membranes containing collagen have been used in the prior art. Abbenhaus et al., *Surg. Forum* 16:477-478 (1965) disclosed collagen films of 2 to 3 millimeter thickness that was produced by heating and dehydrating collagen extracted from cow
10 hides. Chu disclosed non-chemically crosslinked collagen implants produced by compression, which are useful for sustained drug delivery [European Patent Application 187014, published July 9, 1986; U.S. Patent 4,600,533, issued July 15, 1986; U.S. Patent 4,655,980,
15 issued April 7, 1987; U.S. Patent 4,689,399, issued August 25, 1987; and PCT Patent Application WO 90/00060, published June 28, 1989]. Cioca [U.S. Patent 4,412,947, issued November 1, 1983], disclosed an essentially pure collagen sheet made by freeze drying a
20 suspension of collagen in an organic acid. Kuroyanagai et al. [European Patent Application 167828, published January 15, 1984; U.S. Patent 4,642,118, issued February 10, 1987], disclosed an artificial skin composed of two layers: collagen and a poly-alpha-amino
25 acid. Berg et al. [U.S. Patent Application 4,841,962, issued June 27, 1989], disclosed a wound dressing composed of three layers: an adhesive, a cross-linked collagen matrix, and a multilayer polymer film.
- Holman, U.S. Patent 4,950,699, issued August 21, 1990,
30 disclosed a wound dressing consisting of less than 10% collagen mixed with an acrylic adhesive. Cioca et al., British Patent 1,347,582, disclosed a collagenic wound dressing consisting of a freeze dried polydisperse collagen mixture.

35 Steffan et al., European Patent 069260, published January 12, 1983, disclosed a collagen insert

- 3 -

consisting of high purity native collagen. Zimmerman et al. [U.S. Patent 4,453,939, issued June 12, 1984], disclosed a wound healing composition containing collagen coated with fibrinogen, factor XIII fibrinogen, and/or thrombin. Leibovich et al. [U.S. Patent 4,808,402, issued February 1989], disclosed a composition for treating wounds comprising collagen, bioerodible polymer, and tumor necrosis factor. Yannas and Burke [*J. Biomed. Mat. Res.* 14:68-81 (1980)], have reviewed the design of artificial skin, some examples of which contain collagen. Chvapil et al., *Int. Rev. Connect. Tissue Res.* 6:1-61 (1973), particularly at pages 51 to 52; and Pachence et al., *Med. Device and Diag. Ind.*, 2:49-55 (1987), disclose various uses of collagen, including as a drug delivery vehicle.

Most of the previously utilized collagen containing sponges have been used as substrates or skeletons for the growth of cells at a wound site and have not been used for delivery of pharmaceutical agents. The present invention provides a much desired improvement in pharmaceutical sponges by providing for a steady, continuous and sustained release of therapeutic agents over an extended period of time

SUMMARY OF THE INVENTION

The present invention relates to a collagen-containing sponge comprising an absorbable gelatin sponge, collagen, and an active ingredient. Preferably, the absorbable gelatin sponge is a crosslinked gelatin.

Another aspect of the present invention relates to a collagen-containing sponge further comprising one or more of a plasticizer, a stabilizing agent, a drying enhancer or a buffer. Preferably, the plasticizer is selected from polyethylene glycol and glycerol; the stabilizing agent is a sugar selected from the group

- 4 -

consisting of mannitol, lactose and glucose; the drying enhancer is an alcohol selected from the group consisting of ethanol, methanol and isopropyl alcohol; and the buffer is a suitable biological buffer.

- 5 Preferred active ingredients are selected from the group consisting of PDGF, EGF, FGF, PDEGF, PD-ECGF, KGF, IGF-1, IGF-2, TNF, BDNF, CNTF, and NT-3.

Another aspect of the present invention relates to a method of enhancing wound healing of an epidermal
10 wound comprising administration of a wound healing effective amount of an active ingredient via a collagen sponge according to another aspect of the present invention.

Another aspect of the present invention
15 relates to a method of enhancing wound healing of an internal wound comprising administration of a wound healing effective amount of an active ingredient via a collagen sponge according to another aspect of the present invention.

20

DESCRIPTION OF THE DRAWINGS

Figure 1 shows a release profile for PDGF from a dry Gelfoam-Collagen Sponge *in vitro*.

25 Figure 2 shows a release profile for PDGF from a dry Gelfoam-Collagen Sponge *in vitro* showing first order kinetics.

Figure 3 shows the correlation of PDGF measured by radioisotope, ELISA and PDGF bioassay.

30 Figure 4 shows a release profile for PDGF from a wet Gelfoam-Collagen Sponge *in vitro*.

Figure 5 shows a release profile for PDGF from a wet Gelfoam-Collagen Sponge *in vitro* showing first order kinetics.

35 Figure 6 shows the correlation of PDGF measured by a radioisotope, ELISA and PDGF bioassay.

- 5 -

Figure 7 shows a release profile *in vitro* for PDGF from a Gelfoam Sponge without the presence of Collagen.

Figure 8 shows a release profile *in vivo* for PDGF from a Gelfoam-collagen system prepared with 1% collagen solution.

Figure 9 shows a release profile *in vivo* for PDGF from a Gelfoam-collagen system prepared with 8% collagen solution.

Figure 10 shows experimental results obtained by using the rat blood bundle model.

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to a collagen-containing sponge comprising an absorbable gelatin sponge, collagen, and an active ingredient.

An appropriate absorbable gelatin sponge is crosslinked gelatin, for example Gelfoam (Upjohn, Inc., Kalamzoo, Michigan). The absorbable gelatin sponge can be combined with a collagen and active ingredient by soaking the absorbable gelatin sponge in a solution comprising soluble collagen and active ingredient. Alternately, a predetermined amount of a collagen solution can be transferred on top of the gelatin sponge and the solution can be absorbed.

Soluble collagen is collagen that has an average molecular weight of less than 400,000, preferably having a molecular weight of about 300,000. A particularly suitable soluble collagen is Semex S (Semex Medical Co., Malvern, Pennsylvania). This particular soluble collagen is also advantageous because it is the atelopeptide form of the collagen. Atelopeptide collagen is collagen that is free of telopeptide, which is a peptide located at one end of purified collagen often associated with immunogenicity.

- 6 -

A solution of the telopeptide form of collagen can be converted to the atelopeptide form of collagen via hydrolysis using organic acid. Another preferred characteristic of the soluble collagen is that it
5 possesses a minimal amount of crosslinking, i.e., 0.5% or less.

The soluble collagen can be dissolved in a suitable solvent such as water to produce a solution that contains from about 0.5 to about 10% of collagen by
10 weight, preferably from about 1 to about 5% by weight, and more preferably about 2% by weight.

A solution of soluble collagen or a dispersion of collagen fibrils in suspension is used to soak the absorbable gelatin sponge. Typically, a suitable amount
15 of the collagen solution is transferred on top of the absorbable gelatin sponge. In another case, the collagen solution is poured into a container holding the gelatin sponge. Suitable conditions include allowing the soaked sponge to dry at a suitable temperature for a
20 suitable period of time. Generally, the amount of drying time necessary is shorter as the drying temperature is raised. Specifically, a suitable temperature is from about 15°C to 35°C, preferably about room temperature, and a suitable drying time is
25 sufficient time so that the marginal loss of solvent content is essentially zero (e.g., drying time of about an hour to about 10 days, preferably about one to about five days).

To optimize desirable characteristics of a
30 preferred collagen sponge, various additives may be optionally included in the collagen solution. Such desirable characteristics include flexibility, stability, accelerated drying time and a pH compatible with the active ingredient to be utilized.

35 To improve flexibility, a suitable plasticizer can be used. Suitable plasticizers include polyethylene

- 7 -

glycol and glycerol, preferably glycerol. Such plasticizers can be present in an amount from zero to about 100% of the weight of collagen present, preferably from about 10 to about 30% of the weight of collagen present, most preferably about 20% of the weight of collagen present.

To improve the stability of the active ingredient, a suitable stabilizing agent can be used in the film. Suitable stabilizing agents include most sugars, preferably mannitol, lactose, and glucose, more preferably mannitol. Such stabilizing agents can be present in an amount from zero to about 5% of the weight of collagen present, preferably about 1% of the weight of collagen present.

To accelerate drying time for the films, a drying enhancer can be used. Suitable drying enhancers include alcohols, preferably ethanol, methanol and isopropyl alcohol, more preferably ethanol. Such drying enhancers can be present in an amount from zero to about 50% of the weight of the total solution or suspension, preferably from about 10 to about 30% of the weight of the total solution or suspension, more preferably about 20% of the weight of the total solution or suspension.

To produce a pH that is compatible with a particular active ingredient being used, a suitable buffer can be used in the film. Suitable buffers include most of the commonly known and utilized biological buffers, preferably acetate, phosphate and citrate, more preferably acetate and phosphate. Such buffers can be present in an amount of from about 0.01% to about 2% of the weight of the collagen solution or suspension. A compatible pH is one that maintains the stability of an active ingredient, optimizes its therapeutic effect or protects against its degradation. A suitable pH is generally from about 3 to about 8,

- 8 -

preferably about 5 to about 8, and most preferably about neutral pH of from about 7.0 to about 7.5.

Preferred active ingredients are those biological agents which enhance wound healing or regeneration of nerve tissue, particularly recombinant proteins. Such preferred active ingredients include platelet derived growth factor (PDGF), epidermal growth factor (EGF), fibroblast growth factor (FGF), platelet derived epidermal growth factor (PDEGF), platelet derived endothelial cell growth factor (PD-ECGF) keratinocyte growth factor (KGF), insulin-like growth factors 1 and 2 (IGF-1 and IGF-2), tumor necrosis factor (TNF), brain derived neurotrophin factor (BDNF), ciliary neurotrophic factor (CNTF) and neurotrophin-3 (NT-3). A preferred active ingredient is PDGF or PD-ECGF, most preferably PDGF. Such active ingredients are present in an amount sufficient to enhance healing of a wound, i.e., a wound healing effective amount. The actual amount of the active ingredient will be determined by the attending clinician and will depend on various factors such as the severity of the wound, the condition of the patient, the age of the patient and any collateral injuries or medical ailments possessed by the patient. Generally, the amount of active ingredient will be in the range of about 1 $\mu\text{g}/\text{cm}^2$ to 5 mg/cm^2 .

The collagen sponges of the present invention are useful as a means of delivering the active ingredient to cells or tissue with which it is in contact. For example, in the treatment of burns or other traumas to the skin, a collagen sponge can be placed on the wound to deliver a suitable active ingredient to the traumatized area. PDGF is a particularly suitable active ingredient for such uses. Collagen sponges can also be used to accelerate healing of surgical wounds. When used in such a way, the sponge can be placed in the surgical incision and stitched into

- 9 -

the wound as an interface between the two surgical wound surfaces. Collagen sponges can also be used to deliver neurotrophic factors. When used in such a manner, the collagen sponge can be placed in direct contact with or adjacent to the nerve tissue to be treated with the neurotrophic factor.

EXAMPLES

10 Example 1: Preparation of a Collagen Sponge.

A piece of gelatin sponge (Gelfoam®:80 x 250 x 10 mm), was rolled out with a metal rod (diameter: 32 mm, length:130 mm), much like dough to make a thin sheet. The resulting thickness of the sheet was 1mm. Wafers were cut out from the thin sheet with a brass punch. Wafers with a large diameter (diameter:18 mm, weight: 1.5 mg) were cut for *in vivo* studies.

In one study, 0.24 ml or 0.40 ml of the collagen solution containing PDGF was pipetted on top of each wafer. In another study, the wafers were soaked in a collagen solution. The collagen solution containing PDGF was prepared as follows. First, a 4% collagen solution was prepared by dissolving 2 g of a soluble collagen (Semex S Semex, Frazer, Pennsylvania) in 50 ml of distilled water at 30-50°C. To 16 ml of the resulting solution, 0.13 ml of glycerol, 2 ml of alcohol, and 2 ml of a PDGF solution (2 mg/ml acetate buffer) was added. Additionally, a trace amount of ¹²⁵I-PDGF was added to the solution. After the solution was absorbed by each wafer, the wafer was dried overnight to produce a sponge-collagen system containing PDGF.

35

- 10 -

Example 2: Kinetics of Release from Collagen Sponges.

Release rates of active ingredients from collagen sponges were conducted using Coster Transwell Cells ("Cell") (Costar Co., Cambridge, Massachusetts) as follows. Collagen sponges with ^{125}I -PDGF were produced as described in Example 1, and wafers (1.6 cm diameter) were cut from the films. Each wafer was transferred to a Coster Transwell Cell and placed on top of the polycarbonate membrane. 2.5 ml of the receiver solution (water and 1% bovine serum albumin, or water and 0.25% human serum albumin) was added to the Cell holder. The Cells were set on the solution and the release study was initiated. At specified times, 20 μl of the receiver solution was pipetted out and the same amount of fresh solution was replaced in the receiver solution. The sampling procedure was repeated to get another 20 μl sample. The radioactivity of the sample was measured with a gamma counter (Beckman Instruments, Co., Irvine, California). The concentration of protein in the receiver solution at any given time was calculated based on the radioactivity and confirmed using other methods such as ELISA and ^3H -thymidine uptake bioassays. Figures 1 and 2 and 4 and 5 show a typical release profile of PDGF from the wafers. The release profile from the dry gel (Figures 1 and 2) system was very similar to that of the wet gel (Figures 4 and 5) system where the release study was performed immediately after the absorption of the collagen solution by the gelatin sponge. About 80% of the growth factor was released in 100 hours. Data shown in Figures 3 and 6 indicate that the drying process does not change the activity of the growth factor.

Figure 7 shows the release of PDGF from a Gelfoam sponge without the presence of collagen. In this study the release of PDGF from the Gelfoam was

- 11 -

performed. To remove air bubbles trapped inside the membrane while soaking the membrane (thickness: 1 cm) in PDGF solution, the membrane was soaked in water at reduced pressure. The water soaked membrane was
5 equilibrated in PDGF solution. The release rate of PDGF was measured with Costar Transwell cells using ^{125}I -PDGF. The release rate was very fast. Most of the PDGF was released in 12 hours. The results obtained from this study show the combination system of collagen-Gelfoam
10 provides for a steady, continuous and sustained release of therapeutic agents over an extended period of time.

Example 3: Measurement of In Vivo Release Rate of Protein From the Collagen-Sponge System.

15

A. Pre-operative Preparation

Young adult New Zealand White rabbits, weighing approximately 3.0 to 3.5 kg each (M & K Rabbitry, Bentonville, Arkansas) were anesthetized using
20 Rompum® (Farbenfabriken, Bayer, West Germany) as a sedative, followed (10 minutes later) by ketamine (60 mg/kg) and xylaine (5 mg/kg), both administered intramuscularly. Each rabbit's weight was measured and recorded. A small cotton or gauze plug was inserted
25 into both ears of each rabbit, after which the inner surface and outer edges of both ears were shaved using an animal clipper (#40 blade). Commercially available Neet® depilatory cream was then applied to the inner surface of each ear for 10 minutes, after which time it
30 was removed with dry gauze. The inner surface of the ears was wiped with saline-soaked gauze followed by application of a 70% alcohol solution. The dermis of the inner surface on one ear of each rabbit was blanched by infiltration of the ear with a 2% xylocaine solution
35 containing 1:1000 epinephrine (this requires 1.5 to 3.0 mls total volume) using a 30 gauge needle. The

- 12 -

infiltrated area was then scrubbed with 3 cycles of betadine followed by the 70% alcohol solution. Where necessary, the ear plugs were replaced with dry plugs at this point.

5 The rabbits were then transferred to a sterile surgical room. The blanched ear was immobilized on a plexiglass "ear board" (Washington University Medical Center, Division of Technical Services, St. Louis, Missouri) which utilizes two bar clamps, one at the tip
10 and one at the base of the animal's ear, to stabilize the rabbit ear without compromising its blood supply. The animal was draped, and the surgical field (i.e., the inner surface of the blanched ear) sprayed with Betadine and allowed to dry for 3 to 5 minutes.

15

B. Wounding

 Sterile technique was employed throughout the wounding procedure. Using microsurgical instruments, a 6 mm trephine, and a binocular microscope (10x, Zeiss),
20 the surface of the inner ear of each rabbit was scored gently with a 6 mm biopsy punch, and the biopsy site cleared of all tissue and fibers (including the periosreal membrane) down to the level of bare cartilage, using micro-surgical forceps, tenotomy
25 scissors, a blunt edged 2 mm Lempert periosreal elevator, and sterile cotton-tipped applicators. Perichondrium and overlying tissues were removed by dissection. Biopsies in which the cartilage was
- completely cut through by the punch were not used for
30 experimental purposes. However, partial thickness scores of the cartilage were considered acceptable. The location of any nicks or natural holes in the cartilage was carefully noted and recorded (for reference on the harvest day). Blood was removed from the biopsy site
35 with sterile, cotton-tipped applicators, with care taken to avoid excess blood in the wound. Each completed

- 13 -

biopsy was covered with a small piece of saline-soaked gauze. Four viable 6 mm biopsy ulcers were placed on each wounded ear, two on each side of the midline (as defined by the fold in the ear when it was stabilized upon the board). In any event, no more than 5 total biopsies were placed on each ear. The biopsies were positioned a minimum of 1 cm apart.

Upon completion of one ear, the ear was covered with saline-moistened gauze and then taped shut around the gauze to retain moisture until application of PDGF. The second ear was then blanched, scrubbed, immobilized and wounded in the manner as the first ear. Blood was removed from the biopsy site of each second ear and each completed biopsy covered with a small piece of saline-soaked gauze. Upon completion of the second ear, it was covered with saline-moistened gauze until application of PDGF. Any rabbit that showed evidence of recovery from anesthesia at any time prior to this point in the procedure was reanesthetized with 25 mg/kg ketamine, administered intramuscularly.

C. Application of Active Ingredient to Wounds

Wafers prepared by the procedure of Example I were used for *in vivo* drug release study. Small wafers (diameter: 5mm) were used for this experiment. Each wafer was inserted in a wound site (diameter: 6mm) and a piece of Tagaderm® was used to make sure that the wafer remained in the wound site.

The rabbits were allowed to recover from anesthesia under the observation of the investigator performing the surgery. Upon recovery, a plastic neck collar (Canine Center, St. Louis, Missouri) extending approximately 15 to 25 cm outward was placed around each rabbit's neck to prevent the rabbit from disrupting the wounds or dressings. The rabbits were returned to an isolation cage where they were maintained until harvest.

- 14 -

D. Measurement of the Protein Release from the Collagen-Gelatin Sponge System

At selected times, several wafers were taken from the wound sites. New pieces of Tagaderm[®] were used to cover the wound sites where the wafers were removed. The wafers were collected in test tubes. When all the wafers were recovered, the radioactivity of each wafer was counted. The amount of PDGF released at a given time was calculated from the radioactivity of the remaining wafer. Figure 8 shows the release profile of PDGF from the collagen-Gelfoam system which was prepared with 1% collagen solution. After 49 hours, about 62% of PDGF was released. Figure 9 shows the release profile of PDGF from the collagen-Gelfoam system which was prepared with 8% collagen solution. This solution was obtained by dissolving the soluble collagen in distilled water at 60°C. About 73% of PDGF was released after 49 hours.

Example 4: Effect of Collagen-Containing Sponges on New Tissue Growth as Measured by the Rat Blood Bundle Model.

In 30 Lewis rats (125-150 grams), the left tibialis posterior and its parent femoral arterio-venous bundle were dissected from the ankle up to the inguinal ligament. The bundles were sandwiched between two collagen disks 1.6 cm in diameter and placed inside a spoon-shaped silastic mold. Disks from Group A were based on collagen-Gelfoam system. Each disk in the group contained about 125 µg of PDGF. Disks from Group B were based on soluble collagen. Each disk in the group contained about 125 µg of PDGF. Disks from Group C were made of soluble collagen without any PDGF and therefore were used as controls. All the animals were sacrificed at day 30. The contents of the molds were examined grossly, and with a digitizing computer

- 15 -

and 3-D reconstruction, histomorphometrically to determine the volume of tissue generated.

Figure 10 shows the generation of new tissue volumes of three different groups. Substantial increase
5 in new tissue volume was observed in the animals treated with the collagen-Gelfoam system containing 125 µg of PDGF. In the previous experiments using a soluble collagen system with the same animal model, it was found
10 that wafers based on soluble collagen containing PDGF increased the volume of new tissue significantly after implantation between day 10 and day 15. This was especially evident with high doses of PDGF (120 µg/wafer). The study also showed that 30 days after
15 implantation, the new tissue regressed. The current experiments demonstrate that the collagen-Gelfoam system works well for the generation and/or maintenance of new tissue volume for several weeks.

20

* * *

- 16 -

CLAIMS

WHAT IS CLAIMED IS:

5 1. A collagen-containing sponge comprising an absorbable gelatin sponge, collagen, and an active ingredient.

10 2. A collagen-containing sponge according to claim 1 wherein said absorbable gelatin sponge is a crosslinked gelatin.

15 3. A collagen-containing sponge according to claim 2 wherein said crosslinked gelatin is Gelfoam.

 4. A collagen-containing sponge according to claim 3 further comprising a plasticizer.

20 5. A collagen-containing sponge according to claim 4 wherein said plasticizer is selected from polyethylene glycol and glycerol.

25 6. A collagen-containing sponge according to claim 4 further comprising a stabilizing agent.

 7. A collagen-containing sponge according to claim 6 wherein said stabilizing agent is a sugar selected from the group consisting of mannitol, lactose and glucose.

30 8. A collagen-containing sponge according to claim 6 further comprising a drying enhancer.

35

- 17 -

9. A collagen-containing sponge according to claim 8 wherein said drying enhancer is an alcohol selected from the group consisting of ethanol, methanol and isopropyl alcohol.

5

10. A collagen-containing sponge according to claim 8 further comprising a buffer.

11. A collagen-containing sponge according to claim 1 wherein said active ingredient is selected from the group consisting of PDGF, EGF, FGF, PDEGF, PD-ECGF, KGF, IGF-1, IGF-2, TNF, BDNF, CNTF, and NT-3.

12. A collagen-containing sponge according to claim 10 wherein said active ingredient is selected from the group consisting of PDGF, EGF, FGF, PDEGF, PD-ECGF, KGF, IGF-1, IGF-2, TNF, BDNF, CNTF, and NT-3.

13. A collagen film according to claim 11 wherein said active ingredient is PDGF.

14. A collagen film according to claim 12 wherein said active ingredient is PDGF.

15. A method of enhancing wound healing of an epidermal wound comprising administration of a wound healing effective amount of an active ingredient via a collagen sponge according to claim 1.

16. A method of enhancing wound healing of an epidermal wound comprising administration of a wound healing effective amount of an active ingredient via a collagen sponge according to claim 10.

35


- 18 -

17. A method of enhancing wound healing of an internal wound comprising administration of a wound healing effective amount of an active ingredient via a collagen sponge according to claim 1.

5


18. A method of enhancing wound healing of an internal wound comprising administration of a wound healing effective amount of an active ingredient via a collagen sponge according to claim 10.

1/10



2 / 10

Fig 2 PDGF Release from
Gelfoam-Collagen System



3 / 10





FIG. 3


4 / 10

Fig 4 PDGF Release from
Gelfoam-Collagen System



5 / 10

Fig 5 PDGF Release from
Gelfoam-Collagen System



6 / 10





FIG. 6

7 / 10



8 / 10





FIG. 8

ORIGINAL SHEET

9 / 10



10/ 10




FIG. 10

SUBSTITUTE SHEET

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US93/04044

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : A61K 9/70

US CL : 424/488

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/488, 443, 445, 78.06, 801; 514/944, 953

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4,837,285 (BERG ET AL.) 06 JUNE 1989, see entire document.	1-16

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

Special categories of cited documents:	
A document defining the general state of the art which is not considered to be part of particular relevance	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to underlain the principle or theory underlying the invention
E earlier document published on or after the international filing date	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
O documents referring to an oral disclosure, use, exhibition or other means	*Z* document member of the same patent family
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

15 JUNE 1993

Date of mailing of the international search report

11 AUG 1993

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Authorized officer

RAJ BAWA

Facsimile No. NOT APPLICABLE

Telephone No. (703) 308-2351

Form PCT/ISA/210 (second sheet)(July 1992)*